

LUMINOPHORE BYB 400% H.S

Optical Whitener For Cellulosic Fibres

LUMINOPHORE BYB 400% H.S is a highly substantive optical whitening agent for all natural and regenerated cellulosic fibres except acetate. It is applied in hot alkaline liquors and gives particularly strong and brilliant white effects.

Appearance Luminophore BYB 400% H.S is a free flowing bulky Yellow to Greenish powder.

Solubility It is soluble upto 30 g/l at boil.

It is advisable to boil the solution before adding to the treatment baths.

Solutions of 1 g/l Luminophore BYB 400% H.S have a pH of about 9.5.

Affinity Luminophore BYB 400% H.S exhausts from neutral and alkaline baths within the temperature range of 20-120°C. Alkaline liquors above 60°C provide the best exhaustion and development conditions. Its affinity is such that even in liquors without electrolytes often no salt additions are necessary, for eg., in a closed machine.

Regenerated cellulosic fibres do not normally have such good affinity for optical whitening agents as cotton but Luminophore BYB 400% H.S gives a very good yield on them. An addition of 2 g/l glauber's salt anhydrous gives the optimum effect.

Luminophore BYB 400% H.S has good affinity for polyamide 6 above 60°C particularly in the stabilised hydrosulphite bleach bath. Blends of cellulosic and polyamide 6 fibres can therefore be whitened in one bath.

Shade The shade of white obtained is bluish. It is greatly enhanced when applied along with hydrogen peroxide and caustic soda at 70C - 90 C.

Fastness Stability The fastness of the white effect and the stability of Luminophore BYB 400% H.S is listed in the table at the end of the circular.

The excellent wet fastness and very good stability in peroxide bleach baths are particularly interesting features. When the white effects are acidified the shade may tend to yellow but this can be remedied by a weak alkaline rinse. Very slight yellowing may occur in resin finishing, depending on the catalyst and the curing conditions, but this can also be corrected by a weak alkaline rinse.

Hard water has no adverse influence on the white effect. In fact it produces a quicker and more complete exhaustion of the bath. However, iron and, to a far less extent, copper compounds impair the white effect and treatment may be carried out on machines of these metals only if the surfaces have rendered inert.

If there is any risk of iron or copper compounds reaching the whitening bath it is advisable to add a chelating agent. Solutions of Luminophore BYB 400% H.S are sensitive to light. Stock solutions must, therefore, be kept away from light.

LUMINOPHORE BYB 400% H.S

Optical Whitener For Cellulosic Fibres

Application IN BLEACHING: Luminophore BYB 400% H.S is extremely suitable for use in peroxide bleaching (under normal and HT conditions) and in scouring. Optimum levelness, brightness and purity of the white effect are obtained in hot alkaline baths above 80 °C.

If brightening is to be carried out on the pad mangle or by exhaustion at temperatures below 60 °C Luminophore BYB 400% H.S should be used.

IN DYEING: As Luminophore BYB 400% H.S has good fastness properties and a full yield at high temperatures it may also be used with dyes to produce brighter pastel shades.

SOFTENING: Non-ionic and cationic softeners are particularly suitable for goods after they have been optically whitened.

Cationic softeners weaken the white effect slightly but this can usually be compensated by increasing the amount of Optical Whitening Agent.

Stripping To remove the slight brownish shade which occurs and to avoid any subsequent yellowing it is advisable to give the goods a final mild peroxide bleach containing an anionic detergent. If the goods are to be optically whitened again most of the Luminophore brands for cellulosic fibres can be added to this bath.

Complete removal of the white effect can only be obtained by a chlorite bleach.

METHODS OF APPLICATION :

Peroxide Bleach - LUMINOPHORE BYB 400% H.S	%	0.20 - 1.0 owf
Temperature applied under normal bleaching conditions.	°C	85 - 120

Sodium Hydrosulphite Bleach - (CELLULOSE/POLYAMIDE 6 BLENDS) LUMINOPHORE BYB 400% H.S	%	0.1-0.8
Sodium Hydrosulphite	g/l	3-2
PH	pH	7-8
temperature	°C	80-90
time	min.	40-60

Scouring - LUMINOPHORE BYB 400% H.S		
Glauber's salt anhydrous (if necessary)	g/l	2
pH	pH	7-11
temperature	°C	60-95
time	min	30-45

Dye-bath - LUMINOPHORE BYB 400% H.S	%	0.05-0.2 owf
--	---	--------------

If the whitening has been carried out at too low a PH, the weaker white effect obtained can be noticeably improved by an alkaline after treatment.

LUMINOPHORE BYB 400% H.S

Optical Whitener For Cellulosic Fibres

FASTNESS PROPERTIES : -(Luminophore BYB 400% H.S. on the fibre)

light	3-4
washing:test (60° C)	5
washing:test (95° C)	4-5
chlorinebleaching mild	3-4
chlorine bleaching severe	3
chlorine bleaching milk	1
peroxide bleaching	4
perspiration histidine acid and alkaline	5

STABILITY : (Luminophore BYB 400% H.S. in the bath)

hydrogen peroxide	very good
sodium hydrosulphite	very good
sodium chlorite	poor
hydrochlorite pH 11	poor
acid	poor (precipitate)
alkali	very good

The 'standard white' is the maximum white effect obtained on cotton fabric with the product in a peroxide bleach bath. Change in shade is assessed by white scale comparable with the grey scale.

Light fastness is measured upwards from 1 to 8, other fastness properties from 1 to 5.

Fastness properties may differ somewhat according to the pretreatment, the method of application and the degree of whitening.

(Our publications are intended to render information on the best possible application of our products. Recommendations are given according to our best knowledge and belief, but without engagement.)

UNITED Ventures

ventures.united@gmail.com



53, Siddhivinayak, SP-19/20, N.S. Road No. 7
JVPD Scheme, Vile-Parle (W), Mumbai - 400 049
Tel. : 91 - 22 - 2670 1144 • 91 - 21 - 2670 1155

The information given herein and otherwise supplied to users is based on general experience and where applicable, on the results of tests on samples of typical manufacture. However, because of the many factors which are outside our knowledge and control which can affect the use of these products, we can not accept liability for any injury, loss or damage resulting from reliance upon such information